Polyken #930

Tape Coating for Joints & Fittings Market Applications Temperature Range Oil, Gas or Water pipelines Pipeline Rehabilitation Girthwelds for Water, Oil or Gas pipelines Oil or Gas pipelines Figure 12068 class B30

System Description

Polyken #930 is a cold applied tape coating system the corrosion designed for protection of field joints, specialty piping. The products can be used for both buried and above ground applications, and the product is suitable to resist UV irradiation. The unique adhesive retains conformability over a wide temperature range, yet exhibits

an elevated level of shear resistance, which is a key in-ground performance characteristic. Couple with a very maleable polyethylene backing, this versatile tape system can be applied by hand or with a wrapping machine.

Product Advantages

- Heavy duty adhesive Ensures a strong bond & impervious seal.
- Conformable to irregular shapes
 Offers a solution for nearly every application.
- No release liner
 Makes installation fast and easy.
- Worldwide reference lists Established in-ground history.
- Complies with AWWA Standard C-209
 Reliable, high performance corrosion
 protection.
- Compatible with generic plant coating systems
 Versatile.

Product Selection Guide

- Max operating temperature 185°F (85°C)
- Recommended primer 1027 or 1033A
- Additional mechanical layer 955 or 954
- Compatible line coatings PE, FBE, Tape & Coal Tar
- Recommended pipe preparation SSPC-SP2, SP3 & SP6 ST 2 1/2 ST 3
- Performance
 AWWA C-209; DIN30672 & EN12068 class
 B30

Product Construction

- Backing
- Adhesive
- Backing Color

 930-35
 930-50

 6.5 mils (0.165 mm)
 10 mils (0.254 mm)

 28.5 mils (0.724 mm)
 40 mils (1.0.16 mm)

 Black, White*
 Black*

* Other colours are available on request.

Product Properties

Properties	Test Method	Typical Value	
		930-35	930-50
Tensile Strength	ASTM D1000	15 lbs/in. (26 N/cm)	25 lbs/in. (44 N/cm)
Elongation	ASTM D1000	340%	300%
Peel Adhesion to Primed Steel	ASTM D1000	250 oz/in. (27 N/cm)	300 oz/in. (33 N/cm)
Cathodic Disbondment	ASTM G8	0.25 in. radius (6.4 mm)	0.25 in. radius (6.4 mm)
Water Vapor Transmission	ASTM E96B	0.07 perm	0.07 perm
Water Vapor Transmission Rate	ASTM F1249 (100°F, 100% RH)	0.04g/100in. ² /24hr (0.6/m ²)	0.04g/100in. ² /24hr (0.6/m ²)
Volume Resistivity	ASTM E257	2.5 x 10 ¹⁶ ohm•cm	2.5 x 10 ¹⁶ ohm•cm
Dielectric Breakdown	ASTM D1000	650 volts/mil (25.6 kV/mm)	650 volts/mil (23.6 kV/mm)
Dielectric Strength	ASTM D149	21 kV	28 kV
Insulation Ressistance	ASTM D1000	1.4 x 10 ⁷ M ohm	2.0 x 10 ⁷ M ohm
Impact Resistance	EN12068	>8 Nm	>8 Nm
Penetration Resistance	EN12068	Class B30	Class B30

Ordering Information

Polyken 930 Tape Coatings are available in roll form.

930-35 BLK 2 X 50FT 1.5

Tape inner core diameter 1.5, 3" (38, 76 mm)

Tape roll length 50 FT (15 M)

Tape width 1, 2, 5, 6" (25, 50 101, 152 mm)

Tape backing color Black (BLK), White (WHI), Blue (BLU)

Total tape thickness 35, 50 mils (0.89, 1.27 mm)

For other ordering options please contact your Berry Plastics representative.

Equation for Pipe Coating Requirements

(Width of Coating in inches) x (Area of pipe in square feet)*

= Squares** of Coating Required

(Width of Coating in inches - Overlap in inches) x100

(Width of Coating in mm) x (Area of pipe in square meter)*

= Square meters of Coating Required

(Width of Coating in mm - Overlap in mm)

^{*}Area of pipe in square meter = (Diameter in mm) $/1000 \times 3.1416 \times (Length in meter)$



CORROSION PROTECTION GROUP

www.berrycpg.com

The leading global partner in protecting the integrity of critical infrastructure. Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the

usery reasons warrants unterproducely presented within continuity of various the translation project description and is appropriate to use as stated on the respective technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the right.

The information and values listed for Berry Plastics products are averages obtained from the relevant industry test procedures, carried out in our laboratories under controlled conditions. Values obtained on site will vary depending on the test methods and conditions. Manufacturing tolerances are available on request. Whilst Berry Plastics warrants its products to be free of material and manufacturing defects, Berry Plastics disclaims any liability in connection wit the misuse of Berry Plastics products.

Local Distributor / Representative:

For contact details of local Distributors / Representatives Please visit: www.berrycpg.com

Headquarters

Franklin, MA, USA
Tel: +1 508 918 1714
US Toll Free: +1 800 248 0149
Fax: +1 508 918 1910
CPG@berryplastics.com

Houston, TX, USA Tel: +1 713 676 0085 US Toll Free: +1 888 676 7202 Fax:+1 713 676 0086 CPGH@berryplastics.com Tijuana, Mexico
Tel USA +1 858 633 9797
Fax US: +1 858 633 9740
Tel Mexico: +52 664 647 4397
Fax Mexico: +52 664 607 9105
CPGTJ@berryplastics.com

Westerlo, Belgium Tel. +32 14 722500 Fax +32 14 722570 CPGE@berryplastics.com Baroda, India Tel: +91 2667 264721 Fax: +91 2667 264724 CPGIN@berryplastics.com

^{*} Area of pipe in square feet = (Diameter in inches) / $12 \times 3.1416 \times (Length in ft)$

^{**} One Square = One hundred square feet = 9.29 square meters